



Barrier Protection Level	Weight	Color	Material/Construction	Fluid Risk Levels	Water Resistance*	Hydrostatic Pressure**
Level 2	35 GSM	Blue	Full-Length, Non-Woven SMS Unibody Construction	Low-Medium	0.82g (Test Method AATCC 42)	22.0cm (Test Method AATCC 127)
Level 2	43 GSM	Blue	Full-Length, Non-Woven SMS Unibody Construction	Low-Medium	0.70g (Test Method AATCC 42)	33.0cm (Test Method AATCC 127)
Level 2	50 GSM	Blue	Full-Length, Non-Woven SMS Unibody Construction	Low-Medium	0.50g (Test Method AATCC 42)	42.0cm (Test Method AATCC 127)
Level 3	60 GSM	Blue	Full-Length, Non-Woven SMS Unibody Construction	Medium-High	0.33g (Test Method AATCC 42)	51.0cm (Test Method AATCC 127)

\*Measures the resistance of fabrics to the liquid penetration of water by impact

\*\*Measures the resistance of fabrics to the liquid penetration of water by impact under constant and increasing hydrostatic pressure